



Royston®

Technical Data Sheet

DESCRIPTION

Royston Roybond 747 is a primer used with butyl and elastomeric products. Roybond is a liquid adhesive that creates a permanent bond between the tape and the substrate. Roybond 747 can be used for substrate temperatures up to 165°F (74°C). Roybond 747 is available as a liquid that is applied via brush, roller or spray equipment or as an aerosol spray can.

A 4 mil WFT (1.0-1.5 mil DFT) of Roybond 747 or Roybond 747 Aerosol should be applied and allowed to dry prior to application of the tape.

SUBSTRATE COMPATIBILITY

Steel, Stainless Steel, Ductile Iron, other metals, FBE and PE

RECOMMENDED USE

Required for Royston Greenline and Royston Handy Cap products. May be used for other tapes if the compatibility is confirmed through testing.

SURFACE PREPARATION

SSPC SP-2 Hand Tool Cleaning, SSPC SP-3 Power Tool Cleaning or SSPC SP-6/NACE No. 3 Commercial Blast Cleaning

SAFETY

Refer to Material Safety Data Sheet: MSDS-Roybond-747, MSDS-Roybond-747-Aerosol

APPLICATION

Refer to Application Guidelines: AG-COLD-APPLIED-BUTYL-TAPE, AG-Handy-Cap

ROYBOND 747 TYPICAL DATA

Property	Liquid	Aerosol	Test Method
Color	Black	Black	
Dry time	<5 minutes at 70°F (21°C)	<2 minutes at 70°F (21°C)	
Flash Point	38°F (3°C)	0°F (-18°C)	COC
VOC Content	4.98 lb/gal (597 g/L)	5.29 lb/gal (624 g/L)	
Service Temperature Range	-40°F to 165°F -40°C to 74°C	-40°F to 165°F -40°C to 74°C	

ORDERING INFORMATION



Container Size	Containers Per Case	Weight
12oz Spray can	12	15# per Case
1 Quart	6	17# per Case
1 Gallon	4	40# per Case

Calgary : +1 (403) 243-0012
Edmonton : +1 (780) 452-1792
Regina : +1 (306) 721-6933
Brampton : +1 (905) 846-0212

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.

Chase Corporation
295 University Avenue
Westwood, MA 02090

Phone: 800-323-4182
Fax: 781-332-0701
www.chasecorp.com

An ISO 9001:2008
REGISTERED COMPANY